

Product - Data-Sheet

ESBAND Type		FX 20		data-sheet no.
		1st side	2nd side	82001
Carcass		polyester/ cotton special carcass		
Coating		FDA - polyurethane, white ground	textile raw	
Hardness		80 ± 5 Shore A	-/-	
Resistance to abrasion		high	-/-	
Food approved		FDA	-/-	
Coefficient of friction to steel paper		0,4 ± 0,1 μ 0,7 ± 0,1 μ	0,1 ± 0,1 μ 0,3 ± 0,1 μ	
Resistance to temperature		-10 up to + 80 °C		
Antistatic		possible		
Breaking resistance per cm width endless*		1360 N		
Elongation at 10 mm width endless*		30 N	0,1 up to 0,2 %	
		100 N	0,5 up to 0,7 %	
		300 N	2,1 up to 2,6 %	
Strength required for 1% elongation*		165 ± 15 N		
Minimum pulley diameter*		15 mm		
Available sizes standard		length	480 up to 4000 mm	
		width	5,0 up to 900 mm	
		thickness	0,7 up to 0,9 mm	
Tolerances		length	± 0,5 % (min. +/- 2,5 mm)	
		width	± 0,5 mm	
		thickness	± 0,1 mm	
*at smallest thickness				
All data in this data-sheet correspond to the latest state of the art Modifications are possible without prior notice. The values stated are for information only; they do not guarantee a specific property.				Edition: 28.01.2004