

# Product - Data-Sheet

ESBAND Type		FX Elastik		data-sheet no.
		1st side	2nd side	81000
Carcass		polyurethane special carcass		
Coating		FDA - polyurethane, white ground	FDA - polyurethane, white T- profile	
Hardness		80 ± 5 Shore A	80 ± 5 Shore A	
Resistance to abrasion		high	high	
Food approved		FDA	FDA	
Coefficient of friction to steel paper		0,4 ± 0,1 µ 0,7 ± 0,1 µ	0,3 ± 0,1 µ 0,6 ± 0,1 µ	
Resistance to temperature		-10 up to + 80 °C		
Antistatic		no		
Breaking resistance per cm width endless*		auf Anfrage/on request		
Elongation at 10 mm width endless*		10 N	1,8 up to 2,2 %	
		20 N	3,6 up to 4,4 %	
		30 N	5,9 up to 6,9 %	
Strength required for 1% elongation*		3 ± 2 N		
Minimum pulley diameter*		15 mm		
Available sizes standard		length	150 up to 2000 mm	
		width	3,0 up to 400 mm	
		thickness	0,6 up to 3,0 mm	
Tolerances		length	± 1,0 % (min. +/- 2,5 mm)	
		width	± 0,5 mm	
		thickness	± 0,1 mm	
*at smallest thickness				
All data in this data-sheet correspond to the latest state of the art Modifications are possible without prior notice. The values stated are for information only; they do not guarantee a specific property.				Edition: 16.09.2008