

Product - Data-Sheet

ESBAND Type	HTS 14		data-sheet no.
Material	PEEK (100%)		60-14455.0
Tape thickness ⁽¹⁾	0.92 mm		
Surface structure	Tobacco side	very rough	
	Running side	smooth	
Grip on tobacco	good		
Temperature-resistance	up to 200 °C		
Wear resistance	very good		
Air Permeability ⁽²⁾	49 m ³ /h	± 3 m ³ /h	
Breaking strength	400 N/cm	- 8.0 %	
Elongation of endless tape at 150 N/cm pre-tension	0.009	+ 0.3 % - 0.2 %	
Tape widths available	7.2 - 10.2 mm		
Tolerances	length	+ 1 % / - 0 %	
	width	+ 0 mm / - 0.6 mm	
	thickness	+ 0.05 mm / - 0.02 mm	
Recommended for tobacco transport	PROTOS GD 1-2-1		

(1) - Thickness control according to MSN 93.502 (2) - Air permeability control according to MSN 85.001, tape width 9,2 mm

All data in this data-sheet correspond to the latest state of the art.

Modifications are possible without prior notice. The values stated are for information only;

they do not guarantee a specific property.

Edition:
07.03.2017

Copyright ESBAND