

# Product - Data-Sheet

<b>ESBAND Type</b>	<b>KTU 17.1</b>		data-sheet no.  60-171.03
Material	Polyamide		
Tape thickness <sup>(1)</sup>	0.82 mm		
Surface structure	Tobacco side Running side	very rough smooth	
Grip on tobacco	good		
Temperature-resistance	up to 80 °C		
Wear resistance	very good		
Air Permeability <sup>(2)</sup>	43 m <sup>3</sup> /h	± 3 m <sup>3</sup> /h	
Breaking strength	550 N/cm	- 8.0 %	
Elongation of endless tape at 150 N/cm pre-tension	0.022	+ 0.3 % - 0.2 %	
Tape widths available	6.2 - 10.2 mm		
Tolerances	length width thickness	+ 0 % / - 1 % + 0 mm / - 0.5 mm + 0.05 mm / - 0.02 mm	
Recommended for tobacco transport	PROTOS PASSIM	GD 1-2-1 Decouflé D3	
<small>(1) - Thickness control according to MSN 93.502      (2) - Air permeability control according to MSN 85.001, tape width 9,2 mm All data in this data-sheet correspond to the latest state of the art. Modifications are possible without prior notice. The values stated are for information only; they do not guarantee a specific property.</small>			Edition: 27.01.2017  Copyright ESBAND