

Product - Data-Sheet

ESBAND Type	SKO 48.24		data-sheet no.	
Material	Linen		40-4824.01	
Tape surface	plain			
Tape thickness ⁽¹⁾	0.52 mm			
Lateral tape flexibility	very high			
Temperature-resistance	up to 120 °C			
Wear resistance	high			
Breaking strength ⁽²⁾	1020 N/cm	- 8.0 %		
Elongation of endless tape at 150 N/cm pre-tension	0.8 %	± 0.2 %		
coefficient of friction ⁽³⁾	to paper	0.4 μ		± 0.1 μ
	to garniture	0.16 μ		± 0.1 μ
Tolerances	length	+ 1.0 % - 0.0 %		
	width ⁽⁴⁾	+ 0.0 mm - 0.5 mm		
	thickness	+ 0.05 mm - 0.02 mm		
	wobble ⁽⁴⁾	max. 0.8 mm		
		(max. 1.2 mm for tape length exceeding 4000 mm)		
Recommended for Cigarette Production	PROTOS1-8 PROTOS 70, 80, 90, 90E PROTOS 2, 2-2	GD 1-2-1 PASSIM Decouflé 3D		
⁽¹⁾ - At measured pressure of 0,5 N/cm ² ⁽²⁾ - Measured at single sling as per SCHLATTERER norm MSN 77.100 ⁽³⁾ - Average values determined to SCHLATTERER norm MSN 98.105 ⁽⁴⁾ - Measured at a tension of 100N at single sling as per SCHLATTERER norm MSN 81.113 All data in this data-sheet correspond to the latest state of the art. Modifications are possible without prior notice. The values stated are for information only; they do not guarantee a specific property.			Edition: 25.01.2017 Copyright ESBAND	