

Product - Data - Sheet

ESBAND Type	NE 133/1 + PU		data-sheet no. 21310_2
	1st side	2nd side	
Carcass	polyester/ cotton		
Coating	neoprene rubber ground	polyurethane ground	
Hardness ⁶⁾	62 ± 5 Shore A	55 ± 7 Shore A	
Resistance to abrasion	high	high	
Food approved	no	no	
Coefficient of friction to steel ⁵⁾	high	medium	
Resistance to temperature	-20 up to 60 °C		
Antistatic	yes		
Breaking resistance per mm width endless ¹⁾	210 N		
Elongation at 1 mm width endless ¹⁾	3 N 30 N 60 N	0.0 up to 0.1 % 0.5 up to 0.7 % 1.6 up to 2.0 %	
Strength required for 1% elongation at 1 mm width endless ¹⁾	30 ± 3 N		
Minimum pulley diameter ¹⁾	30 mm		
Available sizes standard ²⁾ length ³⁾ width Standard thickness	200 up to 5100 mm 3 up to 420 mm 2.5 mm		
Tolerances length width thickness	± 0,5 % (min ± 2,5 mm) ± 0.5 mm ± 0.1 mm		

¹⁾at standard thickness; ²⁾Possible widths depend on the length to be produced; ³⁾inside length; ⁴⁾still has to be tested; ⁵⁾>0.79 = very high, 0.60-0.79 = high, 0.40-0.59 = medium, 0.20-0.39 = low, <0.20 = very low; ⁶⁾Measured according to DIN ISO 7619-1

All data in this data-sheet correspond to the latest state of the art. Modifications are possible without prior notice. The values stated are for information only, they do not guarantee a specific property.

Edition:
03.02.2020