

Product - Data-Sheet

ESBAND Type	NE 17		data-sheet no. 21702
	1st side	2nd side	
Carcass	aramide		
Coating	neoprene rubber ground	neoprene rubber ground	
Hardness ⁶⁾	62 ± 5 Shore A	62 ± 5 Shore A	
Resistance to abrasion	high	high	
Food approved	no	no	
Coefficient of friction to steel ⁵⁾	high	high	
Resistance to temperature	-20 up to 100 °C		
Antistatic	yes		
Breaking resistance per mm width endless ¹⁾	240 N		
Elongation at 1 mm width endless ¹⁾	30 N 60 N 100 N	0,2 up to 0,4 % 0,5 up to 0,7 % 0,9 up to 1,1 %	
Strength required for 1% elongation at 1 mm width endless ¹⁾	104 ± 5 N		
Minimum pulley diameter ¹⁾	12 mm		
Available sizes standard ²⁾	length ³⁾ width thickness Standard thickness	550 up to 3300 mm 180 up to 5100 mm 3 up to 420 mm 0,9 up to 2,2 mm	
Tolerances	length width thickness	± 0,5 % (min ± 2,5 mm) ± 1,0 % (min ± 2,5 mm) ± 0,5 mm ± 0,15 mm	

¹⁾at standard thickness; ²⁾Possible widths depend on the length to be produced; ³⁾inside length; ⁴⁾still has to be tested; ⁵⁾>0.79 = very high, 0.60-0.79 = high, 0.40-0.59 = medium, 0.20-0.39 = low, <0.20 = very low; ⁶⁾Measured according to DIN ISO 7619-1

All data in this data-sheet correspond to the latest state of the art. Modifications are possible without prior notice. The values stated are for information only, they do not guarantee a specific property.

Edition:
09.07.2021
03.02.2020